



GRAY EPOXY-MASTIC PRIMER MSP-98-04

1.0 DESCRIPTION OF MSP-98-04. This specification covers a one-coat gray epoxy-mastic primer system designed for adhesion to rusty steel, aged galvanized steel and other uses, including uses in contact with freshly poured Portland cement concrete.

1.1 Unless otherwise stated, specification section references are from the version, in effect at the time of this contract, of the Missouri Standard Specifications for Highway Construction and its supplements.

2.0 MATERIAL. The epoxy-mastic shall be a two component modified epoxy containing gray pigmentation and shall comply with the requirements specified herein.

2.1 Pigment. The pigmentation shall be any pigment or combination of pigments formulated to offer the intended protective properties to the cured coating and shall be totally non-reactive to the constituents contained in both cured and uncured Portland cement concrete.

2.2 Vehicle. The vehicle shall be an epoxy type. The curing agent shall have suitable insensitivity to moisture to allow trouble-free application.

2.3 Mixed Paint.

2.3.1 The paint shall be supplied as a two-component material with a 1:1 volume mix ratio and shall be well-ground, not caked, skinned or badly settled in the container. The mixed paint, when applied in one coat, shall be capable of achieving 5 mils dry film thickness without runs or sags.

2.3.2 Pigment. The epoxy-mastic shall contain a minimum of 88 percent solids by weight, when tested in accordance with ASTM D 1644, Method A for 72 hours at 100 F.

2.3.3 Mixed Coating Properties.

Color, Federal Standard 595b	Gray 26373
Weight per gallon, pounds, min.	11.0
Solids, percent by weight, min.	88
Pigment, percent by weight, min.	40
Viscosity, (Krebs-Stormer, 77 F) KU	90 - 120
Volatile Organic Content, lb/gal., max.	3.50
Pot life, 75 F, hours, min.	2
Dry to touch, hours, max.	24
Dry hard, days, max.	7

2.3.4 Shelf Life. The shelf life of the epoxy-mastic shall be a minimum of 12 months.

2.3.5 Resistance Tests. Test panels of steel meeting the requirements of ASTM D 609 having dimensions of 2 x 5 inches x 1/8 inch shall be prepared by sandblasting all surfaces to a white metal condition in accordance with Structural Steel Painting Council SP5 (SSPC-SP5-82). The cleaned panels shall then be exposed to outdoor weather for 30 days or

until uniform rusting occurs. The panels shall then be hand cleaned with a wire brush in accordance with SSPC-SP2-82. A 6 mil dry coating of the epoxy-mastic shall then be applied in one coat in accordance with the manufacturer's current printed instructions. The coating shall be cured as recommended by the manufacturer. Fresh Water, Salt Water, and Weathering and Salt Fog resistance tests as detailed herein shall be performed on one or more test panels. The material will not be approved if any individual test panel fails any of the resistance tests specified herein.

2.3.5.1 Weathering and Salt Fog Resistance. Panels shall be tested in the weatherometer in accordance with ASTM G 23, Type D for 300 hours, starting the test at the beginning of the wet cycle. After this period, the panels shall be removed and scribed with an "X", with at least 2 inch legs, down to base metal. The test panels shall then be tested in accordance with ASTM B 117. After 1000 hours of continuous exposure, the coating shall show no loss of bond, nor shall it show rusting or blistering beyond 1/16 inch from the center of the scribe mark.

3.0 PACKAGING AND LABELING.

3.1 The epoxy-mastic coating shall be packaged in two containers. The components shall be prepackaged such that mixing of a 1:1 ratio, by volume, utilizes a complete container of each component. Each container shall bear a label on which shall be clearly shown the manufacturer, brand name of paint, lot number, date of manufacture and shelf life. The label on the vehicle container shall also include complete instructions for the use of this paint. The container shall be coated, if necessary, to prevent attack by the paint components.

4.0 APPLICATION.

4.1 The epoxy-mastic shall be applied over a SSPC-SP2, SSPC-SP3 or SSPC-SP6 surface preparation, including removal of all rust scale, loose rust, loose mill scale, and loose or non-adherent paint. Oil and grease shall be removed in accordance with SSPC-SP1 Solvent Cleaning.

4.2 The epoxy-mastic shall be applied by spray, brush or roller in accordance with the manufacturer's printed instructions except as herein modified. The contractor shall furnish the engineer a complete set of the manufacturer's printed instructions at least 2 weeks prior to beginning surface preparation.

4.3 The epoxy-mastic shall not be applied when either the temperature of the metal or the air is below 50 F and shall not be applied when the temperature is expected to drop to 40 F or below before the coating has cured or when the steel surface temperature is at or below 5 F above the dew point as determined in accordance with MoDOT Test Method T 38.

4.4 The epoxy-mastic shall be applied in one coat to a 5 mil dry film thickness.

5.0 APPROVAL AND PREQUALIFICATION.

5.1 Manufacturer and Brand Name Approval. Prior to approval and use of gray epoxy-mastic primer, the manufacturer shall submit in triplicate to the Division Engineer, Materials, a certified test report from an approved independent testing laboratory showing

specific test results conforming to all quantitative and resistance test requirements of these specifications. The certified test report shall also contain the exact ratio, by weight, of the pigment component to the vehicle component of the epoxy-mastic used for the tests, the lot tested, the manufacturer's name, brand name of the epoxy-mastic and date of manufacture. Upon approval by the engineer of this certified test report, further resistance tests will not be required, except as hereinafter noted, of that manufacturer for that brand name of epoxy-mastic primer. New certified test results shall be submitted any time the manufacturing process or the epoxy-mastic formulation is changed and may be required by the engineer when sampling and testing of material offered for use indicates nonconformance to any of the requirements herein specified.

5.1.1 Final acceptance of the gray epoxy-mastic primer will be based on a manufacturer's certification submitted in triplicate by the contractor to the engineer and upon results of tests made on samples of the material. The engineer will sample and test each lot of each component prior to approval or use of the material.